

# United States Patent [19]

[11] Patent Number: 4,742,718  
[45] Date of Patent: May 10, 1988

## Jimbo

[34] APPARATUS FOR MEASURING PARTICLE-SIZE DISTRIBUTION

3282548 2/1982 United Kingdom 71/443.5  
0461317 1/1978 U.S.S.R. 75/438

[75] Inventor: Genji Jimbo, Nagoya, Japan  
[73] Assignee: Onoda Cement Company, Ltd., Onoda, Japan

Primary Examiner—Stewart J. Levy  
Assistant Examiner—Robert B. Harris  
Attorney, Agent, or Firm—Price, Hensveld, Cooper, DeWitt & Linton

[21] Appl. No.: 932,853

[22] Filed: Oct. 24, 1986

[30] Foreign Application Priority Data

Oct. 29, 1985 [JP] Japan 60-341793  
Oct. 29, 1985 [JP] Japan 60-341794

[51] Int. Cl. G01N 15/02

[52] U.S. Cl. 73/965.5

[53] Field of Search 73/965.5, 438, 714, 73/438

### References Cited


#### U.S. PATENT DOCUMENTS

1,949,041 8/1934 Vogel-Jurgensen 73/443.5  
3,208,783 9/1965 Mitchell-Kerns 73/443.5  
3,208,784 9/1965 Richard 73/443.5  
3,781,146 1/1974 Hartman 73/461.4  
3,894,460 7/1975 Valenty 73/438  
4,173,426 11/1979 Rosenblum 73/461.4  
4,287,737 9/1981 Boudy et al. 73/443.5  
4,307,609 12/1981 Rosenblum 73/438

#### FOREIGN PATENT DOCUMENTS

0155233 12/1962 Japan 73/438

5 Claims, 4 Drawing Sheets



### DEPR:

FIG. 6 illustrates ratios of error in measuring particle-size distribution in the case when the measurements are conducted at the inserted depths of h.sub.2, h.sub.3 and h.sub.4 with a sample of 1-10 .mu.m in particle size. As can be seen from this figure, the influence of inserted length is weak on the part of finer particles, but the inserted length greatly affects errors in measuring the part of coarser particles. The ratio of errors in measuring in the coarse particle range is smaller when the inserted length is greater.

### DEPR:

FIG. 7 shows a particle-size distribution curve for a representative powder, depicted (in percent) as the ratio of particles remaining in the sieve versus sieve mesh or opening diameter expressed in .mu.m. This curve is divided into three segments to illustrate the portion of particle-size distribution that would be measured by each of three pairs of pressure transmitting tubes inserted at depths h1, h2 and h3 in cells containing identical samples of the powder.

### DEPR:

In addition, when these procedures are adopted, the calculation of a mean value which is usually conducted after measuring multiple samples successively can easily be performed. Further, when different samples are introduced in the respective measuring cells, data and the mean value as well as individual data of different samples can be obtained by only one measuring operation.

### CLPR:

1. An apparatus for measuring particle-size distribution of a powder which comprises: a measuring cell for receiving a suspension of particles to be measured, a rotor on which said measuring cell is mounted in a radial direction, a driving unit for rotating said rotor about an axis of rotation, a pair of parallel pressure transmitting tubes extending in a radial direction into said cell, each of said tubes having opposite tip and base ends, said tip ends of said pressure transmitting tubes inserted from the general direction said axis into said measuring cell with said tip ends at individually different distances from said axis, and a pressure-detecting unit to which said base ends of said pressure transmitting tubes are secured, said pressure detecting unit having a pressure sensitive membrane between said base ends of said tubes for sensing the pressure difference between said base ends of said tubes being adjacent said axis of rotation of said rotor and lying in a plane extending radially thereof, said pressure-detecting unit being electrically connected with a measuring device.

### CLPR:

5. An apparatus for measuring particle-size distribution of a powder which

	U	1	Document ID	Issue Date	Page	Current OR	Current XRef	
1			US 6171743 B1	20010109	9	430/110.3	430/110.4	Electrostat
2			US 5698309 A	19971216	7	428/323	428/220	Molded bod
3			US 4742718 A	19880510	9	73/865.5		Apparatus
4			US 4219589 A	19800826	9	427/213	159/45	Process fo
5			US 4197495 A	19800408	20	324/207.22	266/92	System for